



## C-RAM CS & CS-HT

RoHS  
Compliant

### TECHNICAL BULLETIN 320-8

#### SPACE CLOTH SHEET STOCK WITH CONTROLLED RESISTIVITY AND RF LOSS

C-RAM CS and CS-HT are series of materials with controlled surface resistivity and dissipation factor. Both materials are based on a lightweight woven fiberglass cloth, which is coated with a carbon loaded coating yielding well controlled resistance and RF loss.

C-RAM CS and CS-HT are space cloth type materials exhibiting traditional woven fabric characteristics allowing air and liquids to pass through the material.

Standard C-RAM CS will tolerate continuous use through 215°F.

C-RAM CS-HT is made with a binder which exhibits high thermal breakdown, thus the material will withstand continuous use through 300°F and short time exposure up to 375°F.

C-RAM CS can be provided with a conductive surface, but preferably a non-conductive outer coating is applied for protection and performance consistency. For this reason C-RAM CS is tested and controlled by its insertion loss, measured with the material at a 0° incidence angle.

The following types of C-RAM CS and CS-HT are available:

<u>Grade</u>	<u>Surface Resistance</u>	<u>Insertion Loss at 10 GHz</u>
CS 100	100 ohm/sq.	8.9 dB
CS 377	377 ohm/sq.	3.5 dB
CS 1000	1000 ohm/sq.	1.5 dB
CS 1500	1500 ohm/sq.	1.0 dB

Nominal thickness is .010 in. to .015 in.  
Standard sheet size is 12 in. x 12 in. but can be supplied up to 36 in. x 48 in.

---

This information in this technical bulletin, although believed to be accurate, is not to be taken as a warranty for which Cuming Microwave assumes legal responsibility nor as permission or recommendation to practice any patented invention without license. It is offered for verification by the customer, who must make the final judgment of suitability for any application.

Document Control No. N-08-000-0142-D  
09/11/11 page 1 of 1