



Zinc-rich primer for strong corrosion protection



Zinc Primer

PPG ENVIROCRON[®] PRIMERON[™] ZINC primer is a zinc-rich epoxy powder primer designed to provide enhanced corrosion protection for mild steel, hot-dip galvanized steel and aluminum substrates.

Unlike conventional coatings which form a barrier between the substrate and the environment, *Primeron* ZINC offers added protection through its zinc content. The zinc serves as a sacrificial metal by reacting to corrosive elements, protecting the substrate. *Primeron* ZINC is especially recommended on mechanically pretreated steel, e.g. blasted steel.

Benefits

- Good performance and corrosion prevention up to C5 environments
- Very good flow and appearance
- Low cure capabilities
- Zinc-rich formulation





Performance Comparison

Properties	Test Method	Value
Gloss at 60°	ISO 2813	60-80 gloss units
Specific Gravity	Calculated	2,94 g/cm ³
Impact Resistance	ISO 6272 / ASTM D2794	40 inch-pound - Direct 20 inch-pound - Reverse
Adhesion	ISO 2409	GTO
Conical Mandrel Bending	ISO 6860	0 - 10 mm

Corrosion Performance

Test	Test Method	Substrate	Scribe Corrosion	Surface Defects
NSS (Neutral Salt Spray Test) - 720 h	ISO 9227	Steel pretreated (1)	< 1 mm	No blisters, no rust
		Blasted steel (2)	< 1 mm	No blisters, no rust
CCT (Cyclic Corrosion Testing) - 1680 h	-	Steel pretreated (1)	< 1 mm	No blisters, no rust
		Blasted steel (2)	< 1 mm	No blisters, no rust
Humidity Resistance (40°C, 100% RH) - 720 h	-	Steel pretreated (1)	-	No blisters, no rust
		Blasted steel (2)	-	No blisters, no rust

(1): Chemical pretreatment - Alkaline (Iron phosphate) - Chrome free

(2): Blasted steel - Sanding media: Grit blast, Sanding rating: Sa 2 ½, Rugosity: 6<Ra<12 µm, 50 < Rt <75 µm

Estimated Durability according to ISO 12944 Standard

Pretreatment	Substrate	C2	C3	C4	C5
Chemical	Steel				
Mechanical	Steel				
Chemical	Hot-dip galvanized				
Mechanical	Hot-dip galvanized				

Curing Conditions

Partial Curing	
7 - 10 min	130°C
5 - 7 min	140°C
3 - 5 min	150°C

Full Curing	
25 - 30 min	140°C
20 - 25 min	150°C
15 - 20 min	160°C

This document contains general information only and should not be construed as creating any warranties, express or implied. Please contact a PPG representative for additional information.

The PPG Logo, Envirocron, Secure Launch Excellence and We protect and beautify the world are registered marks of PPG Industries Ohio, Inc. and PPG Primeron is a trademark of PPG Industries Ohio, Inc.
© 2023 PPG Industries, Inc. All Rights Reserved. 01/23 IC237