



# High-performance polyurethane solventborne spray topcoat



## A very robust topcoat offering exceptional durability and versatility

PPG SPECTRACRON® VRP topcoat was designed with polyurethane technology that provides exceptional durability and allows for flexible and efficient OEM application. The topcoat delivers its best performance when paired with *Spectracron VRP* primer, but has the versatility to be used with a variety of other primers. Available in a wide variety colors, *Spectracron VPR* topcoat platform will become the preferred polyurethane solventborne topcoat option for those working in the heavy-duty equipment, transportation and general finishes industries.

### Product Benefits

- Consistently passes premium durability specifications
- Compatibility with broad range of primers
- Wide application window
- 5-minute wet-on-wet application
- Customizable color capability

### Applications

Agricultural equipment

Trailers

Electrical transmission and distribution

Construction equipment





**Product Characteristics**

Color	Multiple
Gloss @ 60° (ASTM D523)	> 85
VOC*	3.5 lbs./gal.
Applications	Cold-rolled steel, hot-rolled steel, aluminum, cast iron

**Performance Properties**

Xenon Arc Weather-O-Meter* (2,200 hours, SAE J2527)	>85% gloss retention at 20° >95% gloss retention at at 60° $\Delta E \leq 1$
Hardness (ASTM D3363)	>6H
Primer-to-Substrate Adhesion* (ASTM D3359)	4B
Intercoat Adhesion* (ASTM D3359)	5B
Conical Mandrel (1/8", ASTM D522)	Pass, no cracking
Chemical Resistance (500 hours: diesel, water, oil immersion; ASTM D1308)	Pass

\* Results will vary based on pigment package used to obtain specific colors.



The technical data presented in this document is based upon information believed by PPG to be currently accurate. However, no guarantees of accuracy, comprehensiveness or performance are given or implied. Continuous improvements in coatings technology may cause future technical data to vary from what is in this document. Contact your PPG representative for the most up-to-date information.

The PPG Logo, We protect and beautify the world and Spectracron are registered trademarks of PPG Industries Ohio, Inc. ©2023 PPG Industries, Inc. The IN Logo is a registered trademark of LinkedIn Corporation. All rights reserved. 04/23 IC125

